


Multi-lube



Technical Data




AMBERSIL MULTI-LUBE is a multi-purpose lubricant which lubricates, removes moisture, and protects against corrosion. Excellent material compatibility for use in almost any general lubrication role. Specifically formulated for use in automotive applications.



TECHNICAL DATA

Appearance	: Amber coloured liquid.
Odour	: White spirit.
SG @ 20°C (aerosol)	: 0.71
Pressure @ 20°C	: 3.6 bar.
Discharge rate 20°C	: 1.2 g/s
Temperature range	: -20°C to +115 °C
Corrosion protection	: 200 hours in BS3900 F4 salt spray test.
Solubility	: Soluble in hydrocarbon solvents, insoluble in water.
Compatibility	: Safe on most paints, rubber, plastics and painted surfaces
Flammability	: Classified as extremely flammable under current EU regulations.
Flashpoint	: Not applicable in sealed aerosol.
Packaging	: 500 ml aerosol (12 per carton).

PART NUMBER:
6170030020



STORAGE

The product may be stored at normal ambient temperatures and has a shelf life of not less than 72 months with correct storage. Aerosols should always be stored below 50°C, away from direct heat and naked flame.

HEALTH AND SAFETY

Health and Safety sheet available separately.

TECHNICAL SERVICE

CRC Industries UK Ltd provides a technical support service and maintains a constant programme of research and development. We are able to assist customers by specific product development to meet particular requirements.

MISREPRESENTATION ACT 1967 TRADE DESCRIPTIONS ACT 1968

The information given in this publication is based on our experience and reports from customers. There are many factors outside our control and knowledge which affect the use and performance of our products and for which reason no warranty is given, express or implied. Users should make their own tests to determine the applicability of such information or the suitability of any products for their own particular purposes. Statements concerning the use of the products described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is to be assumed.